# RAM RATNA INTERNATIONAL

**(ISO 9001-2008)**

Ram Ratna House, Oasis Complex, P.B. Marg, Worli, Mumbai – 400 013 (India)

Tel: +91-22-2494 9009 / 2492 4144, Fax: 2493 0203 / 2339


---

# VENTAN R 100 AMS

**T.I.Notes**

**VENTAN R 100 AMS** is amphoteric replacement syntan for use in leather industry.

## CHARACTERISTICS:

| | | |
|---|---|---|
| Appearance | : | Pale yellow coloured powder |
| % moisture content | : | 5.0 max. |
| Solubility | : | Freely soluble in water giving clear to slightly hazy soln. |
| pH of 10% solution | : | 3.0 - 4.0 |
| % Acidity | : | 5.0 max. |

## SPECIAL FEATURES:

- It being amphoteric, can be used at both lower and higher pH.
- It gives good softness and fullness without loading the leather.
- It improves the evenness of the milling grain.
- Its use in retanning facilitates brilliant dyeing shades.
- It can be used in combination with synthetic, vegetable and chrome tanning agents.

## APPLICATION :

The recommended dosage is 2 - 3 %, on shaved wt., for upper leathers in Rechroming.
The recommended dosage is 6-8 %, on shaved, for furniture leather.
The recommended dosage is 4 - 8 %, on shaved wt., for sheep & goat garment nappa leather.

## STORAGE STABILITY:

More than one year if stored properly at ambient temperature in supplied packing.

---